

decomur Super Bonding Filler

decomur Super-Haftspachtel Premium-Qualitaet

Synthetic resin modified, gypsum-based joint filler for indoor use and optimum processing characteristics. Very good bonding, even on critical surfaces.

Instructions for use:

decomur Super Bonding Filler is ideally suited for filling cracks and holes, for all-over smoothing and for gluing and jointing gypsum board panels. Gypsum board panels mounted stress-free smoothed with *decomur Super Bonding Filler* do not require reinforcing strips (gauze). Always observe the gypsum board manufacturer's instructions for use. *decomur Super Bonding Filler* can be used on all mineral surfaces such as plaster, stone, concrete, air-entrained concrete, masonry, etc.

decomur Super Bonding Filler can be stretched to nothing and uniformly cures no matter the thickness of the applied layer, without forming sinks or cracks.

decomur Super Bonding Filler provides optimum surfaces for the following wall-papering and painting works as is it water vapour permeable.

Not suitable for filling glass, plastic, wood, metal and emulsion pain surfaces.

Technical specifications:

Basic raw materials:	Synthetic resin, methyl cellulose, natural gypsum
Bulk density:	approx. 0.83 g/cm ³
pH-value:	7-8
Mix ration:	1.8-2.2 parts by volume powder to 1 part by volume water (e.g. 1 kg powder in 600 ml water)
Consumption:	1 kg powder per m ² with thickness of 1 mm
Working time:	approx. 45 Min. at 20° Celsius
Tensile bending strength:	387 N to CE EN 13963-4B
Fire behaviour	A1 to CE EN 13963
CE-conform according to	CE EN 13963-4B

Preparation of surface:

The surface must be dry, firm and free of release agents (dust, formwork oil, etc.). Remove old wallpapers and flaking coats of paint with *decotric Wallpaper Remover*. Remove loose plaster. Prime highly absorbent, sanding and chalking surfaces with *decotric Deeply Penetrating Primer – Solvent Free*.

Instructions for use:

Pour clean, cold water into a container and sprinkle in *decomur Super Bonding Filler*. Stir vigorously until a smooth, lump-free mortar results. Use a firmer consistency to fill cracks and holes than for widespread filling. The filling compound can be applied with a filling knife or trowel after 2-3 minutes maturing time.

Minor unevenness can be removed using a wet sponge board before the filler has completely hardened. After the filler has completely dried out the surface can be reground. It may be necessary to prime the improved areas or the whole surface using *decotric Deeply Penetrating Primer – Solvent Free* to avoid uneven drying of subsequent coats of paint of improving works.

Do not use if the surface and/or room temperature is less than +5° Celsius. Clean tools in water immediately after use.

Storage:

Store in a dry place! Keep the containers tightly sealed!

Available sizes:

500 g paper box	003901001
1 kg paper box	003902001
2 kg paper box	003903001
5 kg paper bag	003905001
10 kg paper bag	003904001
25 kg paper bag	003906001