

# **Power Paste Normal Paper**

#### Instructions for use:

*Power Paste Normal Paper* is suitable for pasting light weight wallpapers.

# **Technical specifications:**

Components:	Modified starch, methyl cellulose, additives
Density:	approx. 0.40 g/cm <sup>3</sup>
pH-value:	approx. 8
Solubility:	Ready for use in 30 minutes
Usage:	approx. 200 ml/m <sup>2</sup>

#### Substrate preparation:

The surface must be dry, firm, and dust and grease-free. Remove old, peeling wallpapers and distempers using *decotric Wallpaper Remover*. Make good cracks and holes using *Power MT 75*.

Pre-treat highly absorbent, sanding and chalking surfaces using *decotric Deeply Penetrating Primer – Solvent Free* or *Power Primer PP*. Water-soluble contaminations in the surface, which could show through when wallpapered over, should be isolated using *decotric Insulating Spray*. We recommend applying a sub-coat of *Power Wallpaper Primer* before hanging highly translucent wallpapers and where surfaces are highly contrasting

### **Application:**

Add 10 kg powder into a bucket with 6 I cool clean water and mix it. Stir compound again after 3 minutes.

The filler remains processable for approx. 60 minutes. The application of a thick layer in one single workstep is possible. It will not shrink or crack when it dries. The filler is easy to smooth and after drying easy to sand. To avoid irregular drying of subsequent coatings on partial filled areas the filled spots or even the entire wall should be primed again with *decotric Primer – solvent-free or Power Wall-Primer* 

## Note:

Please see EU safety data sheet for all safety-related data (EU-CLP)

Do not use at building fabric and room temperatures below + 5  $^{\circ}\mathrm{C}$ 

Clean tools with water after use.

# Mixing ratio:

for	Mixing ratio	Quantity of water per 125 g packet	Coverage of a 125 g packet
Pre-pasting	1 : 65	81	60-80 m²
Lightweight wallpapers	1 : 52	6-7 I	30-35 m²

#### Storage:

Store in cool, dry place, out of reach of children.

Available size: 125 g collapsible box

ble box 002801173

Minimum durabiity: 5 years as of date of manufacture



decotric GmbH - Im Schedetal 1 - 34346 Hann. Muenden - Germany - www.decotric.com Note:

As of 2025-08-07

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.